COLORPRINT PU EXTRA

Description

PU heat seal material with polyester backing, created for inkjet digital printing & cutting systems with solvent, eco solvent or Latex based inks. Suggested for “difficult” fabrics such as windbreakers, K-Way, nylon, leather, sports bags, umbrellas.
The material is certified Öko-Tex® Standard 100 Class I

Average film thickness : **120 micron**

Usage informations

Due to the many different base materials available on the market, the following instructions are given as a guideline only :
Plotter settings (eg. with ROLAND VP-300)
Blade: ***new at 45°***
Minimum cutting pressure: ***80 gf***
Transfer setup
Temperature: ***155* °C** *(310°F)*
Time: ***15 seconds***
Pressure: ***medium (3÷4 bar)***

Procedure

Print and cut the material
Weed the exceeding material
Remove the print from the polyester backing using Siser’s T.T.D. Easy (adhesive, transparent and resistant to high temperatures)
Heat apply
Remove the application tape warm (should you use other application tapes, follow the manufacturer’s instructions)

Certifications

The product is REACH compliant.
The product is certified Öko-Tex® Standard 100 Class I

FIDUCIA NEL TESSILE
Testato per sostanze nocive
secondo Oeko-Tex® Standard 100
1400240.O CENTROCOT

Suitable textiles

Polyamide, cotton, nylon and treated materials (not suited for dye sublimation fabrics)

Washing instructions

Wait **24h** after the heat transfer
60°C - inside out
Do not use bleach or other aggressive chemical agents.
Dry clean: **no**
Tumble dry: **yes**

TÜVRheinland CERTIFIED Management System ISO 9001:2008 www.tuv.com ID 9105027958

Siser s.r.l.

N.B. All information given in this sheet are based on our experience.
We always recommend performing a test before starting standard production.
For best results we recommend to store the product away from direct sunlight.

sportstil

The product meets the Italian and EU regulations relating to its proper use, and to the (EU) regulation n. 1907/2006/EU REACH (Registration, Evaluation, Authorization and Restriction of Chemical substance).
This document can be subject to variations. Updated versions are available on our website www.siser.it.
For further information, please contact our Sales Office.
Thank you.